

KA 70 Injection Blend

Application:	Hot Metal desulfurization	
Composition:	CaC ₂	68-72 %
	Coal	4-6 %
	Lime	rest
Granulation:	< 0,063 mm	min. 80 %
	< 0,090 mm	min. 95 %
Density:	Approx. 1.000 kg * m ⁻³	
Special Properties:	Very good flowability enabling exact dosage	

