

KM 110 L (smooth) Injection Blend

Application:	Desulfurization of hot metal
Composition:	10 % Mg alloy 90 % reactive, soft-burned lime with ultralow sulfur content
Granulation:	<u>Magnesium alloy</u> > 1,0 mm 0 % > 0,8 mm max. 5 % 0,5 – 0,8 mm max. 10% 0,2 – 0,5 mm 25-50 % < 0,2 mm rest <u>Lime</u> < 0,1 mm 100 %
Bulk Density:	approx. 1.000 kg/ m ³
Special Properties:	Good flowability due to special additives

