

ALMAMET

January 2015

Mg 99, 9

Application: Raw Material for Injection Blend Hot Metal desulfurization

Composition: Mg: 99,95 %; Al: 0,0019%; Mn: 0,0187 %; Cu: 0,0006%; Fe: 0,0009%; Si: 0,027%; Ni: 0,0008%

Grain size:

| | |
|------------|--------|
| > 1.0 mm | 0% |
| 0.5-1.0 mm | 35-60% |
| 0.2-0.5mm | 35-60% |
| < 0.2mm | traces |

Density: Ca 800 kg*m⁻³

Packing: Big Bags

