

## Magnesium Powder MGP 0 – 100µm

<b>Application:</b>	Pyrotechnics						
<b>Composition:</b>	Made from Mg min. 99,90 %						
<b>Granulation:</b>	Mg powder 0/100 µm Typical sieve analysis to JEL 200 sieve inlet: DIN 3310-1  <table><tr><td>&gt; 100 µm</td><td>max.10%</td></tr><tr><td>&gt; 63 µm</td><td>40-70 %</td></tr><tr><td>&lt; 63 µm</td><td>min.30%</td></tr></table>	> 100 µm	max.10%	> 63 µm	40-70 %	< 63 µm	min.30%
> 100 µm	max.10%						
> 63 µm	40-70 %						
< 63 µm	min.30%						
<b>Apparent Density:</b>	0,55 – 0,65 kg / dm <sup>3</sup>						
<b>Special Properties:</b>	Due to a special production procedure a low oxide content is achieved						
<b>Packaging:</b>	UN-CERTIFIED 210-L STEEL DRUMS						

